

In the Claims:

Cancel claims 5-11 without prejudice or disclaimer and amend claims 1-4 and 12, as follows:

Sub B2

2

A

1007881.021202

1. (Amended) A method for producing an optical lens comprising, adding 2-(2-hydroxy-4-octyloxyphenyl)-benzotriazole to a monomer selected from the group consisting of a diethylene glycol bisallylcarbonate monomer, a thiourethane monomer and a episulfide monomer to form a mixture, and polymerizing the monomer in the mixture to form the optical lens, wherein the optical lens has a yellowness index (YI) between about 0.7 and 1.6 and a 380 nm UV transmittance of at most 30 % when the monomer is a diethylene glycol bisallylcarbonate monomer and a thickness of the optical lens is about 2.2 mm, wherein the optical lens has a yellowness index (YI) between about 0.7 and 1.6 and a 380 nm UV transmittance of at most 30 % when the monomer is a thiourethane monomer and a thickness of the optical lens is about 2.2 mm and wherein the optical lens has a yellowness index (YI) between about 0.7 and 1.8 and a 400 nm UV transmittance of at most 30 % when the monomer is a episulfide monomer and a thickness of the optical lens is about 1.8 mm.

2. (Amended) The method of claim 1, further comprising casting the mixture into a mold for a lens before the polymerizing of the monomer to form the optical lens.

Sub B3

3. (Amended) An optical lens comprising 2-(2-hydroxy-4-octyloxyphenyl)-benzotriazole and a polymer formed by polymerizing a monomer selected from the group consisting of a diethylene glycol bisallylcarbonate monomer, a thiourethane monomer and a episulfide monomer.

4. (Amended) The optical lens of claim 3, wherein said optical lens absorbs long-wave UV rays having a wavelength of around 400 nm.

12. (Amended) Spectacles comprising the optical lens according to claim 3, 4 or 13.

Add new claim 13, as follows:

A4
Sub B3

13. The optical lens according to claim 3,
wherein the optical lens has a yellowness index (YI) between about 0.7 and 1.6 and a 380
nm UV transmittance of at most 30 % when the monomer is a diethylene glycol
bisallylcarbonate monomer and a thickness of the optical lens is about 2.2 mm,
wherein the optical lens has a yellowness index (YI) between about 0.7 and 1.6 and a 380
nm UV transmittance of at most 30 % when the monomer is a thiourethane monomer and a
thickness of the optical lens is about 2.2 mm and
wherein the optical lens has a yellowness index (YI) between about 0.7 and 1.8 and a 400
nm UV transmittance of at most 30 % when the monomer is a episulfide monomer and a
thickness of the optical lens is about 1.8 mm

END
A4

2021 FEB 1 02:12:00